






ACRYLAC[®]


SPECIAL RUB EXTRA 57S1108

Protective coating with excellent rub resistance

Properties

Water-based coating for offset printing applications with coating unit

ACRYLAC SPECIAL RUB EXTRA	57S1108
Gloss	
Rub resistance	
Blocking resistance	
Drying	
COF (dyn.)	

 = positive rating point on a scale from zero to max. ten points for highest value / best suitability

Property / Suitability	Guide value	Test condition / Remarks
Mass density	1,05 g/cm ²	+/- 0,05
pH-value	7,5 – 8,5	
Viscosity (upon delivery)	35 – 43 s	cup drain time in ref. to DIN 53211, Ø 4 mm, 20°C
Hot-foil embossing capability *	yes	
Applicable double-sided *	yes	
UV-coatable *	no	Recommendation: production test
Glueable *	yes	Recommendation: keep glue flaps free of coating
Block-sealable ¹	yes	PP-film, uncoated, at 130°C / 1 s / 10 kPa.

The data provided are typical values but do not represent a binding specification.

*) Further information can be taken from the following pages, under the headline „Notes about Coating Properties on the Printed Sheet“

1) Referring to seal-strength we recommend a pre-test with the exact material used in the print run.

Acrylate coated films are inept for sealing.

Storage/Handling

- store in unopened, original container under cool and frost free conditions (0° C – 30° C)
- shelf life 12 months, if unopened; use quickly after opening original container
- viscosity can increase during storage; check before use; dilute with 1-5% water if required
- **stir well before use**; check homogeneity

Processing Advice

- recommended application rate: 4 – 6 g/m² (wet)
- soft plates/blankets recommended
- excessive pumping without consumption on press must be avoided
- delivery stack temperatures above 35°C can lead to blocking
- do not mix with different coating products
- clean coating circuit thoroughly; avoid contamination of coating with rinse residues

Appropriate Press Configuration for Converting

- sheet-fed offset press with coating unit (chambered blade and anilox roller)
- hot-air blow drier with steam-extraction

Suitable Substrates

Paper and cardboard, coated, absorbent

Suitable Printing Inks

- alkali resistant acc. to ISO 2836 (Magenta usually suitable, despite its missing resistance)
- resistance against alcohol and solvent mixture recommended
- changes in colour/hue of the used printing inks can occur, if the pigments therein are featuring insufficient resistance properties

Auxiliaries

Thinning: Water / Cleaning: 10T0145 / Defoaming: 10MGA0423

General Information

In case potentially disruptive influences can occur, such as those originating from packaging contents or external influences (e.g. solvents, detergents, grease, moisture, etc.), the suitability of the coating needs to be double-checked through appropriate testing. For consistent print results, we recommend regular in-depth cleaning of the anilox rollers.

Notes about Coating Properties on the Printed Sheet

- the final surface properties have established not before complete drying of ink and coating
- the glueability is also influenced by substrate, ink and glue.
- coated areas are sealed and wet glue takes notably longer to set there, compared to setting on the uncovered substrate surface; our recommendation: keep glue flaps free of coating
- for finishing, metallic inks have to be tape resistant
- finishing with UV-coating or hot-foil stamping requires a stable substrate surface
- adhesion and scratch resistance of the UV-coating or hot foil stamping can vary, depending on the substrate surface quality, the ink, and/or the applied UV-coating/hot-foil
- the values for CoF and block-sealing resistance (if provided) are assessed under defined testing conditions. Depending on printing- and accompanying ambient conditions, the values may vary.
- suitability for two-sided printing can be reduced by the substrate, high ink coverage and slow-setting colours. In these cases we recommend a sufficient airing and drying times before perfecting

Information about Printing Food Packaging

This water-based coating is not of the "low-migration" type and is not recommended for food packaging printing.

Labelling/Safety

See material safety data sheet

How supplied

25-kg plastic hobbock
150-kg plastic drums
1000-kg IBC

Contact addresses for advice and further information can be found under www.hubergroup.com

This Technical information sheet reflects the current state of our knowledge. It is designed to inform and advise. We assume no liability for correctness. Modifications may be made in the interest of technical improvement.